

## China Rotary Kiln Calcined Bauxite

Chemical Compositions (%)	Items	Specification
	Al <sub>2</sub> O <sub>3</sub>	86 Min
	Fe <sub>2</sub> O <sub>3</sub>	1.7 Max
	SiO <sub>2</sub>	7.2 Max
	TiO <sub>2</sub>	3.4 Max
	CaO+MgO	0.31 Max
	Na <sub>2</sub> O+K <sub>2</sub> O	0.21 Max
	H <sub>2</sub> O	0.29 Max
Physical Propertis	Bulk density (gr/cm <sup>3</sup> )	3.22

Available Sizes			
0-0.1 mm	0-1 mm	1-3 mm	3-5 mm
Package:Big Bag			

Other Size and Specifications are Available as Desired by Customers